



SANSIN PROTECTIVE COATING KP-11

DESCRIPTION A concentrated penetrating, aqueous, low VOC coating. For use as a long-term protective undercoat for millwork and wood products that are subject to potential wet conditions. Sansin KP-11 is designed to prevent swelling and moisture absorption. KP-11 conforms to WDMA-I.S.4 testing methods.

APPLICATIONS Recommended for use after being diluted with water in a ratio of 1:1.

CHARACTERISTICS

- ◆ Appearance..... Transparent Amber
- ◆ Odor..... Low
- ◆ Form Liquid
- ◆ Specific Gravity..... 1.00-1.02
- ◆ Density 8.42 lbs.
- ◆ Solid Content..... 20-24%
- ◆ pH, (approx.) 8.4-8.9
- ◆ Viscosity, 60cPs @20°C, Brookfield spindle #1, 60 RPM
- ◆ Solvents Low
- ◆ Diluent..... Water
- ◆ Cleanup..... Soap & Water
- ◆ Drying Time (To touch) @ 20°C (68°F)..... 4-6 Hours
- ◆ Coverage pending. For example; application method, wood species, and dipping time all contribute to different uptakes.
- ◆ Keep from freezing

PRODUCT BENEFITS

- ◆ Water dilutable
- ◆ Water Repellent for millwork
- ◆ Environmentally Responsible
- ◆ Low VOC
- ◆ Non Flammable
- ◆ Provides dimensional stabilization
- ◆ Penetrates the wood surface
- ◆ Low odor
- ◆ Does not discolor the wood
- ◆ No surface residues on wood
- ◆ Good Paint Adhesion
- ◆ Mortar Resistant

PACKAGING Available in 5 US gallon plastic containers, 50 US gallon drums, 1000 litre totes and bulk.

APPLICATION METHODS

- ◆ Apply by 30, 90, or 180 sec. dip depending to quality required. Vacuum coating and spraying are also possible.

WORKING PROCEDURE

- ◆ Apply the product evenly
- ◆ Applicable over wood products with moisture content of 8-20%
- ◆ Allow **4–6 hours** of drying time @ 20°C (68°F)
- ◆ Stir container lightly to raise eventually settled neutral material.
- ◆ Add water to the product applying moderate agitation.
- ◆ For best results dilute the product with water (15-20°C) in the ratio of 1:1.

STORAGE

Store at a temperature of between + 5°C and + 25 °C (41°F and 77°F).
 Keep containers tightly closed.
 Cover the dipping tank when not in use.

SAFETY

See Material Safety Data Sheet

The information contained in this document is given in good faith based on our current knowledge. The use of the product is beyond the control of The Sansin Corporation, and no guarantees, expressed or implied, are made as to the result to be obtained if not used in accordance with the published Directions for Use. The Sansin Corporation does not assume any legal responsibility for use or reliance on same. This information must on no account be used as a substitute for necessary field tests, which alone can ensure that the product is suitable for the expected use. Before using any product, read its label.